



中国认可
国际互认
检测
TESTING
CNAS L6069



Test Report

Report No. TC.23.05.002033

Date of Issue 05/15/2023

Applicant: Caledonian Cables Limited

Applicant address: 1/F., CMA Building, 64-66 Connaught Road Central, Hong Kong

Description of the test subject:

Sample	Description	Photo
001	<p>Sample Description: COAXIAL RF 7/8" 50 Ω</p> <p>Style No.: COAXIAL RF 7/8" 50 Ω</p> <p>Manufacturer: Caledonian Cables Limited</p>	

Receipt Date of Sample: 05/06/2023

Date of Testing: From 05/07/2023 to 05/10/2023

Sample submitted: The sample(s) was (were) submitted by applicant and identified.

Conclusion:

Test Items			Conclusion
No.	Items	Standard	
1	Vertical flame spread of vertically-mounted bunched wires or cables	IEC 60332-3-22:2018	Pass
2	Single flame propagation	IEC 60332-1-2:2004+A1:2015	Pass

Note: (1) The TÜV SÜD SW Rail Transportation Technology (Jiangsu) Co., Ltd. General Terms & Conditions applied, for full content please visit <https://www.tuvsud.cn/zh-cn/terms-and-conditions>. (2) The results relate only to the sample(s) as received. (3) The test report shall not be reproduced except in full without the written approval of the company.

Laboratory:
TÜV SÜD SW Rail Transportation
Technology (Jiangsu) Co., Ltd.



Phone: +86/ (0) 519- 8123-9872
Fax: +86/ (0) 519- 8123-9872 ext.123
E-mail: czx.qm@tuvsud.com
www.tuvsud.com

Regd. Office:
Innovative Industry Park, No. 377 Wuyinan Road,
National High and New Technology & Industry
Development Zone, Wujin, 213015 P.R. China



中国认可
国际互认
检测
TESTING
CNAS L6069



Test Report

Report No. TC.23.05.002033

Date of Issue 05/15/2023

Test Results

1. IEC 60332-3-22:2018 Tests on electric and optical fibre cables under fire conditions— Part 3-22:Test for vertical flame spread of vertically-mounted bunched wires or cables—Category A

1.1 Sample details

Length of test sample (m)	3.5
Cable diameter (mm)	28.0
Non-metallic volume per metre of test sample (L)	7
Range of conductor cross-sections (mm ²)	≤35
Number of strands in the bundle	1
Number of bundles	25
Number of layers	3
Number of burners	1
Positioning of test pieces	Touching
Flame application time (min)	40

Precondition	Temperature (°C)	Humidity (%)	Duration (h)
	20±10	50±20	≥16

1.2 Test results

Measurements/ observation	Result
The extent of damage(m)	0.92

Requirement:

The maximum extent of the charred portion measured on the sample shall not have reached a height exceeding 2.5m above the bottom edge of the burner.

Conclusion: Pass

Note: (1) The TÜV SÜD SW Rail Transportation Technology (Jiangsu) Co., Ltd. General Terms & Conditions applied, for full content please visit <https://www.tuvsud.cn/zh-cn/terms-and-conditions>. (2) The results relate only to the sample(s) as received. (3) The test report shall not be reproduced except in full without the written approval of the company.

Laboratory:
TÜV SÜD SW Rail Transportation
Technology (Jiangsu) Co., Ltd.



Phone: +86/ (0) 519- 8123-9872
Fax: +86/ (0) 519- 8123-9872 ext.123
E-mail: czx.qm@tuvsud.com
www.tuvsud.com

Regd. Office:
Innovative Industry Park, No. 377 Wuyinan Road,
National High and New Technology & Industry
Development Zone, Wujin, 213015 P.R. China



中国认可
国际互认
检测
TESTING
CNAS L6069



Test Report

Report No. TC.23.05.002033

Date of Issue 05/15/2023

2. IEC 60332-1-2:2004+A1:2015 Tests on electric and optical fibre cables under fire conditions- Part 1-2: Test for vertical flame propagation for a single insulated wire or cable - Procedure for 1 kW pre-mixed flame

2.1 Sample details

Length of test sample (mm)	600
Cable diameter (mm)	28.0

Precondition	Temperature (°C)	Humidity (%)	Duration (h)
	23±5	50±20	≥16

2.2 Test results

Measurements/ observation	1 st Test
The distance between the lower edge of the top support and the onset of charring (mm)	325
The distance between the lower edge of the top support and the charring downwards (mm)	420

Note: If a failure is recorded, two more tests shall be carried out. If both tests result in passes, the single insulated conductor or cable shall be deemed to have passed the test.

Requirement:

- 1) The distance between the lower edge of the top support and the onset of charring is greater than 50 mm.
- 2) Charring extends downwards to a point less than 540 mm from the lower edge of the top support.

Conclusion: Pass

Statement: The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential smoke and toxicity hazard of the product in use. Test results are just for internal reference.

TÜV SÜD SW Rail Transportation Technology (Jiangsu) Co., Ltd.

Drafted by:

Approved by:

Jinqiang Zhou

Wayne Wang

-End of Report-

Note: (1) The TÜV SÜD SW Rail Transportation Technology (Jiangsu) Co., Ltd. General Terms & Conditions applied, for full content please visit <https://www.tuvsud.cn/zh-cn/terms-and-conditions>. (2) The results relate only to the sample(s) as received. (3) The test report shall not be reproduced except in full without the written approval of the company.

Laboratory:
TÜV SÜD SW Rail Transportation
Technology (Jiangsu) Co., Ltd.



Phone: +86/ (0) 519- 8123-9872
Fax: +86/ (0) 519- 8123-9872 ext.123
E-mail: czx.qm@tuvsud.com
www.tuvsud.com

Regd. Office:
Innovative Industry Park, No. 377 Wuyinan Road,
National High and New Technology & Industry
Development Zone, Wujin, 213015 P.R. China